## PT REPORT

Number: RIAB86.48 - Final

Page 1 of 2

Description RIAB - Ring Investigation Identification Asbestos in Bulk Materials.

Participant CRB Analyse Service GmbH

Bahnhofstrasse 14 37181 Hardegsen

Germany

Method and evaluation

The PT was organised in accordance with document: Protocol RIAB.

After obtaining the reference value, the samples have been shipped to the

participants laboratory.

The reported results of the participant are compared with the reference values.

The results of the comparison are presented on page 2.

Policy statement: The evaluation reports of VSL's proficiency testing schemes are provided for the purpose of communicating the proficiency demonstrated by participants on specific measurements and/or calibrations. The reports are intended to be used in support of demonstrating competence in measurement or calibration, fulfilling quality control requirements as stipulated in written standards on showing such competence, and claims of calibration and measurement capabilities.

Delft, 12 July 2021 VSL B.V.

R.P. van Otterloo Metrology Project manager comparisons

www.vsl.nl

## PT REPORT

Number: RIAB86.48 - Final

Page 2 of 2

Period of ILC May 2021 – July 2021

## Results & Evaluation

|               | 8601    |           | 8602    |           |
|---------------|---------|-----------|---------|-----------|
| Fibre type    | Results | Reference | Results | Reference |
| Chrysotile    | 10-15%  | 2-5%      | < 0.1%  | < 0.1%    |
| Amosite       | 15-30%  | 15-30%    | < 0.1%  | < 0.1%    |
| Crocidolite   | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Tremolite     | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Actinolite    | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Anthophyllite | < 0,1%  | < 0,1%    | < 0.1%  | < 0.1%    |

Points: 8 Points: 10

|               | 8603    |           | 8604    |           |
|---------------|---------|-----------|---------|-----------|
| Fibre type    | Results | Reference | Results | Reference |
| Chrysotile    | 10-15%  | 10-15%    | 5-10%   | 2-5%      |
| Amosite       | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Crocidolite   | 5-10%   | 2-5%      | < 0.1%  | < 0.1%    |
| Tremolite     | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Actinolite    | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
| Anthophyllite | < 0.1%  | < 0.1%    | < 0.1%  | < 0.1%    |
|               |         | •         |         |           |

Points: 10 Points: 10

Results The result with a total score of 95 is satisfactory

